

**PolyOne Synprene® RT-3975 Thermoplastic Elastomer - SBC (discontinued \*\*)**

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

**Material Notes:**

Description/Features:High Performance Thermoplastic ElastomerUV StabilizedNaturalApplications:Multi-

PurposeMarket:AutomotiveBuilding and ConstructionConsumer GoodsIndustrialProcessing Method:Injection MoldingExtrusionPolyOne

First ChoiceInformation provided by PolyOne Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Synprene-RT-3975-Thermoplastic-Elastomer-SBC-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_PolyOne-Synprene-RT-3975-Thermoplastic-Elastomer-SBC-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	Instant; ASTM D2240
Tensile Strength, Yield	8.69 MPa	1260 psi	Method A (Dumbbell & Section), 20 in/min, Break; ASTM D412
	5.52 MPa @Strain 300 %	800 psi @Strain 300 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Elongation at Break	570 %	570 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Rebound	46 %	46 %	Bayshore; ASTM D2632
Tear Strength	50.8 kN/m	290 pli	Die C (graves), 20 in/min; ASTM D624
Compression Set	20 %	20 %	Method B, 73°F(23°C), 22 hrs; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-62.0 °C	-79.6 °F	ASTM D746

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China