

## PolyOne Synprene® RT-5155 Thermoplastic Elastomer - SBC (discontinued \*\*)

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

### Material Notes:

Description/Features:High Performance Thermoplastic ElastomerNaturalIgnition ResistantApplications:Multi-PurposeMarket:Building and ConstructionConsumer GoodsIndustrialProcessing Method:Injection MoldingPolyOne First ChoiceInformation provided by PolyOne Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Synprene-RT-5155-Thermoplastic-Elastomer-SBC-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_PolyOne-Synprene-RT-5155-Thermoplastic-Elastomer-SBC-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	Instant; ASTM D2240
Tensile Strength, Yield	4.07 MPa	590 psi	Method A (Dumbbell & Section), 20 in/min, Break; ASTM D412
	2.45 MPa @Strain 300 %	355 psi @Strain 300 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Elongation at Break	580 %	580 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Rebound	43 %	43 %	Bayshore; ASTM D2632
Tear Strength	22.1 kN/m	126 pli	Die C (graves), 20 in/min; ASTM D624
Compression Set	13 %	13 %	Method B, 73°F(23°C), 22 hrs; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-56.0 °C	-68.8 °F	ASTM D746
Flammability, UL94	V-0	V-0	Natural, 0.062 in thick; UL 94
Oxygen Index	27 %	27 %	0.062 in. bars; ASTM D2863

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China