

PolyOne Synprene® ST-6120 Thermoplastic Elastomer - SBC (discontinued **)

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

Material Notes:

Description/Features:High Performance Thermoplastic ElastomerTransparentOver-Molding GradeApplications:Multi-PurposeFDA (Food Contact)Market:Consumer GoodsProcessing Method:Injection MoldingPolyOne First ChoiceDisclaimer: A thermoplastic elastomer compound formulated for use in food contact applications. The physical properties listed above are typical values obtained on laboratory prepared samples and tested in accordance with accepted test methods. All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21 for use in the packaging of food. The listings cover many uses and restrictions may apply depending on the application. PLEASE CONTACT US TO REVIEW THE SUITABILITY OF SPECIFIC PRODUCTS IN SPECIFIC APPLICATIONS. This statement is only an overview of the FDA listings for this product. IT IS THE CUSTOMER'S RESPONSIBILITY TO ENSURE THAT THE COMPOUND IS SUITABLE FOR ITS INTENDED APPLICATIONS.Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Synprene-ST-6120-Thermoplastic-Elastomer-SBC-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	20	20	Instant; ASTM D2240
Tensile Strength, Yield	3.17 MPa	460 psi	Method A (Dumbbell & Section), 20 in/min, Break; ASTM D412
	0.621 MPa @Strain 300 %	90.0 psi @Strain 300 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Elongation at Break	760 %	760 %	Method A (Dumbbell & Section), 20 in/min; ASTM D412
Tear Strength	8.77 kN/m	50.0 pli	Die C (graves), 20 in/min; ASTM D624

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

