

## PolyOne Trilliant™ HC HC3220-0030 RS Natural Polycarbonate (PC)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

The Trilliant® specialty compounds offer a complete system of specialty engineered materials, certified processes, services and technical support that enable healthcare OEM's to get to market ahead of the competition. When specified, Trilliant® compounds may incorporate agency rated materials that meet USP Class VI, FDA or ISO 10993 testing requirements. Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Trilliant-HC-HC3220-0030-RS-Natural-Polycarbonate-PC.php](http://www.lookpolymers.com/polymer_PolyOne-Trilliant-HC-HC3220-0030-RS-Natural-Polycarbonate-PC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	117 MPa	17000 psi	Type I, 51 mm/min; ASTM D638
Elongation at Break	9.0 %	9.0 %	Type I, 51 mm/min; ASTM D638
Flexural Strength	186 MPa	27000 psi	ASTM D790
Flexural Modulus	7.24 GPa	1050 ksi	ASTM D790
Izod Impact, Notched	1.20 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	2.25 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Melting Point	288 - 310 °C	550 - 590 °F	
Deflection Temperature at 0.46 MPa (66 psi)	>= 143 °C @Thickness 3.18 mm	>= 289 °F @Thickness 0.125 in	Annealed; ASTM D648

Processing Properties	Metric	English	Comments
Mold Temperature	65.6 - 76.7 °C	150 - 170 °F	
Drying Temperature	93.3 °C	200 °F	
Dry Time	3.00 hour	3.00 hour	

Descriptive Properties	Value	Comments
Agency Ratings	USP Class VI	
Appearance	Natural Color	
Features	Biocompatible	
	Good Chemical Resistance	
	Good Colorability	
	Good Impact Resistance	
	Specialty Grade	
Filler / Reinforcement	Glass Fiber Reinforcement, 30% Filler by Weight	
Forms	Pellets	
Generic Material	PC	
Generic Name	Polycarbonate (PC)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Hospital Goods	
	Housings	
	Medical Appliances	
	Medical/Healthcare Applications	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China