

PolyOne Trilliant™ HC X HC5200-0028 XR Gray Styrene Butadiene Block Copolymer (SBC)

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Trilliant-HC-X-HC5200-0028-XR-Gray-Styrene-Butadiene-Block-Copolymer-SBC.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.79 g/cc	2.79 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	46	46	ASTM D2240
Tensile Strength, Yield	1.17 MPa	170 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	250 %	250 %	Type I, 5.1 mm/min; ASTM D638

Processing Properties	Metric	English	Comments
Melt Temperature	163 - 204 °C	325 - 399 °F	
Mold Temperature	15.6 - 37.8 °C	60.1 - 100 °F	
Drying Temperature	76.7 °C	170 °F	

Descriptive Properties	Value	Comments
Appearance	Grey	
Features	High Specific Gravity	
	Non-Toxic	
Forms	Pellets	
Generic Material	SBC	
Generic Name	Styrene Butadiene Block Copolymer (SBC)	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value America	Comments
	South America	
Uses	Industrial Applications	
	Medical/Healthcare Applications	
	Radiation Shielding	
	Weighting & Balancing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China