

Polycasa Acryl® G 88 E Acrylic

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Same as Lucryl G 88, but higher resistance to stress cracking and higher processing viscosity. Used for: extruded protective layer on PVC, ABS and PC for outdoor applications, as well as bath tubs and shower trays. Data was collected by ISO methods. Quinn Manufacturing Group rebranded its Plastics Division as Polycasa in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polycasa-Acryl-G-88-E-Acrylic.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	
Moisture Absorption at Equilibrium	0.30 %	0.30 %	
Linear Mold Shrinkage, Flow	0.0065 cm/cm	0.0065 in/in	
Melt Flow	0.90 g/10 min @Load 3.80 kg, Temperature 230 °C	0.90 g/10 min @Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	75.0 MPa	10900 psi	
Elongation at Break	4.5 %	4.5 %	
Tensile Modulus	3.30 GPa	479 ksi	
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 20.0 °C	38.9 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	103 °C	217 °F	
Deflection Temperature at 1.8 MPa (264 psi)	98.0 °C	208 °F	
Vicat Softening Point	108 °C	226 °F	
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.2	3.2	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	60.0 kV/mm	1520 kV/in	
Dissipation Factor	0.030	0.030	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.040	0.040	
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China