

Polykemi AB POLYblend 85V PC/ABS-Blend, Flame Retardant

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYblend-85V-PCABS-Blend-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	With Flow; ISO 2577
	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	Across Flow; ISO 2577
Melt Index of Compound	25 g/10 min	25 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 260 °C	@Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Elongation at Yield	4.5 %	4.5 %	ISO/R527
Flexural Strength	<= 95.0 MPa	<= 13800 psi	ISO 178
Flexural Modulus	2.40 GPa	348 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	2.50 J/cm ²	11.9 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	108 °C	226 °F	120°C/h; ISO 75/1
Vicat Softening Point	120 °C	248 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Thermal Properties	960 °C Metric	1760 °F English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 280 °C	464 - 536 °F	
Mold Temperature	70.0 - 100 °C	158 - 212 °F	
Drying Temperature	80.0 - 100 °C	176 - 212 °F	
Dry Time	2 - 8 hour	2 - 8 hour	in circulation dryer
	2 - 8 hour	2 - 8 hour	in fresh-air dryer
	2 - 8 hour	2 - 8 hour	in desiccant air dryer
Injection Pressure	90.0 - 150 MPa	13100 - 21800 psi	
Back Pressure	0.500 - 1.50 MPa	72.5 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-50	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China