

## Polykemi AB POLYelast TPE HJ753 Thermoplastic Elastomer, PP/Elastomer, Mineral Reinforced

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-POLYelast-TPE-HJ753-Thermoplastic-Elastomer-PPElastomer-Mineral-Reinforced.php](http://www.lookpolymers.com/polymer_Polykemi-AB-POLYelast-TPE-HJ753-Thermoplastic-Elastomer-PPElastomer-Mineral-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in <sup>3</sup>	ISO 1183
Filler Content	15 %	15 %	±2%; Polykemi
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	With Flow; ISO 2577
	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	Across Flow; ISO 2577
Melt Index of Compound	14 g/10 min	14 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 24.0 MPa	<= 3480 psi	ISO/R527
Elongation at Break	160 %	160 %	ISO/R527
Elongation at Yield	9.0 %	9.0 %	ISO/R527
Flexural Strength	<= 36.0 MPa	<= 5220 psi	ISO 178
Flexural Modulus	2.30 GPa	334 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	1.60 J/cm <sup>2</sup>	7.61 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 - 65.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	30.6 - 36.1 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	Polykemi
Deflection Temperature at 0.46 MPa (66 psi)	100 $^{\circ}\text{C}$	212 $^{\circ}\text{F}$	120 $^{\circ}\text{C}/\text{h}$ ; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	57.0 $^{\circ}\text{C}$	135 $^{\circ}\text{F}$	120 $^{\circ}\text{C}/\text{h}$ ; ISO 75/1
Vicat Softening Point	53.0 $^{\circ}\text{C}$	127 $^{\circ}\text{F}$	50 $^{\circ}\text{C}/\text{h}$ ; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
	130 $^{\circ}\text{C}$	266 $^{\circ}\text{F}$	50 $^{\circ}\text{C}/\text{h}$ ; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 250 $^{\circ}\text{C}$	446 - 482 $^{\circ}\text{F}$	
Mold Temperature	40.0 - 60.0 $^{\circ}\text{C}$	104 - 140 $^{\circ}\text{F}$	
Injection Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China