

Polykemi AB POLYelast TPE Z805P Thermoplastic Elastomer, SEBS-based

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYelast-TPE-Z805P-Thermoplastic-Elastomer-SEBS-based.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.014 - 0.020 cm/cm	0.014 - 0.020 in/in	With Flow; ISO 2577
	0.014 - 0.020 cm/cm	0.014 - 0.020 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	Polykemi
	@Time 15.0 sec	@Time 0.00417 hour	

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 220 °C	356 - 428 °F	
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	
Back Pressure	0.500 - 1.50 MPa	72.5 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	Low	% of injection pressure
Injection Pressure	Low	
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China