

## Polykemi AB POLYelast TPE Z900 Thermoplastic Elastomer, SEBS-based

Category : Polymer , Thermoplastic , Elastomer, TPE

**Material Notes:**

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-POLYelast-TPE-Z900-Thermoplastic-Elastomer-SEBS-based.php](http://www.lookpolymers.com/polymer_Polykemi-AB-POLYelast-TPE-Z900-Thermoplastic-Elastomer-SEBS-based.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.017 - 0.024 cm/cm	0.017 - 0.024 in/in	With Flow; ISO 2577
	0.017 - 0.024 cm/cm	0.017 - 0.024 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	Polykemi
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength at Break	<= 14.0 MPa	<= 2030 psi	ISO/R527
Elongation at Break	450 %	450 %	ISO/R527
100% Modulus	0.00450 GPa	0.653 ksi	ISO/R527
300% Modulus	0.00620 GPa	0.899 ksi	ISO/R527
Tear Strength	45.0 kN/m	257 pli	D624

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 220 °C	356 - 428 °F	
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	
Back Pressure	0.500 - 1.50 MPa	72.5 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ( )	Low	% of injection pressure
Injection Pressure	Low	
Injection Speed ( )	High	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China