

Polykemi AB POLYfill PP EIP5025 F VT2 Polypropylene, Mineral Reinforced, Extrusion grade, Low CLTE

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PP-EIP5025-F-VT2-Polypropylene-Mineral-Reinforced-Extrusion-grade-Low-CLTE.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ISO 1183
Filler Content	25 %	25 %	±2%; Polykemi
Linear Mold Shrinkage	0.0090 - 0.011 cm/cm	0.0090 - 0.011 in/in	With Flow; ISO 2577
	0.0090 - 0.011 cm/cm	0.0090 - 0.011 in/in	Across Flow; ISO 2577
Melt Index of Compound	5.0 g/10 min	5.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 22.0 MPa	<= 3190 psi	ISO/R527
Elongation at Yield	6.0 %	6.0 %	ISO/R527
Flexural Strength	<= 40.0 MPa	<= 5800 psi	ISO 178
Flexural Modulus	1.90 GPa	276 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	120°C/h; ISO 75/1
Vicat Softening Point	73.0 °C	163 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
	149 °C	300 °F	50°C/h; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China