

Polykemi AB POLYfill PPC GF15030 PD2 Polypropylene Copolymer, Glass Fiber Reinforced, Chemically Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPC-GF15030-PD2-Polypropylene-Copolymer-Glass-Fiber-Reinforced-Chemically-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183
Filler Content	30 %	30 %	±2%; Polykemi
Melt Index of Compound	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 70.0 MPa	<= 10200 psi	ISO/R527
Elongation at Break	4.0 %	4.0 %	ISO/R527
Flexural Strength	<= 110 MPa	<= 16000 psi	ISO 178
Flexural Modulus	5.00 GPa @Temperature 23.0 °C	725 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	1.00 J/cm ² @Temperature 23.0 °C	4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	120°C/h; ISO 75/1
Vicat Softening Point	120 °C @Load 5.001 kg	248 °F @Load 11.03 lb	50°C/h; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
Glow Wire Test	750 °C @Thickness 2.00 mm	1380 °F @Thickness 0.0787 in	IEC 695-2-1

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China