

Polykemi AB POLYfill PPC K5025 PP, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPC-K5025-PP-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	ISO 1183
Filler Content	25 %	25 %	±2%; Polykemi
Melt Index of Compound	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 20.0 MPa	<= 2900 psi	ISO/R527
Elongation at Yield	7.0 %	7.0 %	ISO/R527
Flexural Strength	<= 35.0 MPa	<= 5080 psi	ISO 178
Flexural Modulus	1.60 GPa @Temperature 23.0 °C	232 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.500 J/cm ² @Temperature 23.0 °C	2.38 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	103 °C	217 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	62.0 °C	144 °F	120°C/h; ISO 75/1
Vicat Softening Point	70.0 °C @Load 5.001 kg	158 °F @Load 11.03 lb	50°C/h; ISO 306
	135 °C @Load 1.00 kg	275 °F @Load 2.21 lb	50°C/h; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Thermal Properties	750 °C Metric	1380 °F English	Comments
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China