

Polykemi AB POLYfill PPC T5020 Polypropylene Copolymer, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 20% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPC-T5020-Polypropylene-Copolymer-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Filler Content	20 %	20 %	±2%; Polykemi
Linear Mold Shrinkage	0.010 - 0.013 cm/cm	0.010 - 0.013 in/in	Across Flow; ISO 2577
	0.010 - 0.013 cm/cm	0.010 - 0.013 in/in	With Flow; ISO 2577
Melt Index of Compound	5.0 g/10 min	5.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 25.0 MPa	<= 3630 psi	ISO/R527
Elongation at Yield	8.0 %	8.0 %	ISO/R527
Flexural Strength	<= 38.0 MPa	<= 5510 psi	ISO 178
Flexural Modulus	1.90 GPa	276 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	58.0 °C	136 °F	120°C/h; ISO 75/1
Vicat Softening Point	58.0 °C	136 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	

Thermal Properties	Metric	English	Comments
	@Load 1.00 kg	@Load 2.21 lb	50°C/h, ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in desiccant air dryer
	2 - 4 hour	2 - 4 hour	in circulation dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	
Scratch Resistance, 10N (dL)	3.3	10N Fine Structure; ISO 1518/D65
	3.8	10N Rough Structure; ISO 1518/D65
	4.4	20N Fine Structure; ISO 1518/D65
	5.3	20N Rough Structure; ISO 1518/D65

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China