

Polykemi AB POLYfill PPH B8065 VT1 Polypropylene Homopolymer, Mineral Reinforced, Heat Resistant

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-B8065-VT1-Polypropylene-Homopolymer-Mineral-Reinforced-Heat-Resistant.php

Physical Properties	Metric	English	Comments
Density	1.86 g/cc	0.0672 lb/in ³	ISO 1183
Filler Content	65 %	65 %	±2%; Polykemi
Linear Mold Shrinkage	0.011 - 0.014 cm/cm	0.011 - 0.014 in/in	With Flow; ISO 2577
	0.011 - 0.014 cm/cm	0.011 - 0.014 in/in	Across Flow; ISO 2577
Melt Index of Compound	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 18.0 MPa	<= 2610 psi	ISO/R527
Elongation at Yield	5.0 %	5.0 %	ISO/R527
Flexural Strength	<= 35.0 MPa	<= 5080 psi	ISO 178
Flexural Modulus	3.20 GPa @Temperature 23.0 °C	464 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.200 J/cm ² @Temperature 23.0 °C	0.952 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	145 °C	293 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	120°C/h; ISO 75/1
Vicat Softening Point	100 °C @Load 5.001 kg	212 °F @Load 11.03 lb	50°C/h; ISO 306
	150 °C	302 °F	

Thermal Properties	Metric @Load 1.00 kg	English @Load 2.21 lb	50°C/h· ISO 306 Comments
--------------------	-------------------------	--------------------------	-----------------------------

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China