

## Polykemi AB POLYfill PPH GF8030 HC Polypropylene Homopolymer, Glass Fibre-Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-POLYfill-PPH-GF8030-HC-Polypropylene-Homopolymer-Glass-Fibre-Reinforced.php](http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-GF8030-HC-Polypropylene-Homopolymer-Glass-Fibre-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in <sup>3</sup>	ISO 1183
Filler Content	30 %	30 %	±2%; Polykemi
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	With Flow; ISO 2577
	0.0080 cm/cm	0.0080 in/in	Across Flow; ISO 2577
Melt Index of Compound	5.0 g/10 min	5.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 103 MPa	<= 14900 psi	ISO/R527
Elongation at Break	4.0 %	4.0 %	ISO/R527
Elongation at Yield	3.5 %	3.5 %	ISO/R527
Flexural Strength	<= 158 MPa	<= 22900 psi	ISO 178
Flexural Modulus	8.00 GPa	1160 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	3.90 J/cm <sup>2</sup>	18.6 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	159 °C	318 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	149 °C	300 °F	120°C/h; ISO 75/1
Vicat Softening Point	143 °C	289 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
	166 °C	331 °F	50°C/h; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China