

## Polykemi AB POLYfill PPH T15040 Polypropylene Homopolymer, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-POLYfill-PPH-T15040-Polypropylene-Homopolymer-Mineral-Reinforced.php](http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-T15040-Polypropylene-Homopolymer-Mineral-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	ISO 1183
Filler Content	40 %	40 %	±2%; Polykemi
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	With Flow; ISO 2577
	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	Across Flow; ISO 2577
Melt Index of Compound	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 29.0 MPa	<= 4210 psi	ISO/R527
Elongation at Yield	4.0 %	4.0 %	ISO/R527
Flexural Strength	<= 58.0 MPa	<= 8410 psi	ISO 178
Flexural Modulus	3.90 GPa @Temperature 23.0 °C	566 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.150 J/cm <sup>2</sup> @Temperature -20.0 °C	0.714 ft-lb/in <sup>2</sup> @Temperature -4.00 °F	ISO 179
	0.200 J/cm <sup>2</sup> @Temperature 23.0 °C	0.952 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	120°C/h; ISO 75/1
Vicat Softening Point	88.0 °C	190 °F	50°C/h; ISO 306

Thermal Properties	@Load 5.001 kg Metric	@Load 11.03 lb English	Comments
	148 °C	298 °F	50°C/h; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Processing Properties	Metric	English	Comments
Melt Temperature	205 - 260 °C	401 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China