

Polykemi AB POLYfill PPH TS15040 D Polypropylene Homopolymer, Mineral Reinforced, Detergent Resistant

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-TS15040-D-Polypropylene-Homopolymer-Mineral-Reinforced-Detergent-Resistant.php

| Physical Properties | Metric | English | Comments |
|------------------------|--------------------------------------|--------------------------------------|-----------------------|
| Density | 1.22 g/cc | 0.0441 lb/in ³ | ISO 1183 |
| Filler Content | 40 % | 40 % | ±2%; Polykemi |
| Linear Mold Shrinkage | 0.0090 - 0.011 cm/cm | 0.0090 - 0.011 in/in | With Flow; ISO 2577 |
| | 0.0090 - 0.011 cm/cm | 0.0090 - 0.011 in/in | Across Flow; ISO 2577 |
| Melt Index of Compound | 15 g/10 min | 15 g/10 min | ISO 1133 |
| | @Load 2.16 kg, Temperature 230 °C | @Load 4.76 lb, Temperature 446 °F | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-------------------------|----------------------------|----------|
| Tensile Strength at Break | <= 30.0 MPa | <= 4350 psi | ISO/R527 |
| Elongation at Yield | 6.0 % | 6.0 % | ISO/R527 |
| Flexural Strength | <= 55.0 MPa | <= 7980 psi | ISO 178 |
| Flexural Modulus | 3.20 GPa | 464 ksi | ISO 178 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| Charpy Impact, Notched | 0.400 J/cm ² | 1.90 ft-lb/in ² | ISO 179 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |

| Thermal Properties | Metric | English | Comments |
|---|----------------|----------------|-------------------|
| Deflection Temperature at 0.46 MPa (66 psi) | 120 °C | 248 °F | 120°C/h; ISO 75/1 |
| Deflection Temperature at 1.8 MPa (264 psi) | 75.0 °C | 167 °F | 120°C/h; ISO 75/1 |
| Vicat Softening Point | 80.0 °C | 176 °F | 50°C/h; ISO 306 |
| | @Load 5.001 kg | @Load 11.03 lb | |
| | 145 °C | 293 °F | |

| Thermal Properties | Metric @Load 1.00 kg | English @Load 2.21 lb | 50°C/h: ISO 306 Comments |
|--------------------|------------------------------|---------------------------------|-----------------------------|
| Flammability, UL94 | HB @Thickness 1.60 mm | HB @Thickness 0.0630 in | |
| Glow Wire Test | 750 °C @Thickness 2.00 mm | 1380 °F @Thickness 0.0787 in | IEC 695-2-1 |

| Processing Properties | Metric | English | Comments |
|-----------------------|-----------------|------------------|------------------------|
| Melt Temperature | 205 - 260 °C | 401 - 500 °F | |
| Mold Temperature | 40.0 - 80.0 °C | 104 - 176 °F | |
| Drying Temperature | 70.0 - 80.0 °C | 158 - 176 °F | |
| Dry Time | 2 - 4 hour | 2 - 4 hour | in circulation dryer |
| | 2 - 4 hour | 2 - 4 hour | in desiccant air dryer |
| Injection Pressure | 40.0 - 110 MPa | 5800 - 16000 psi | |
| Back Pressure | 1.00 - 2.00 MPa | 145 - 290 psi | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|-------------------------|
| Holding Pressure () | 20-40 | % of injection pressure |
| Injection Speed () | High | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China