

Polykemi AB POLYfill PPHC T5040 Polypropylene, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPHC-T5040-Polypropylene-Mineral-Reinforced.php

| Physical Properties | Metric | English | Comments |
|------------------------|--------------------------------------|--------------------------------------|-----------------------|
| Density | 1.23 g/cc | 0.0444 lb/in ³ | ISO 1183 |
| Filler Content | 40 % | 40 % | ±2%; Polykemi |
| Linear Mold Shrinkage | 0.0080 - 0.012 cm/cm | 0.0080 - 0.012 in/in | With Flow; ISO 2577 |
| | 0.0080 - 0.012 cm/cm | 0.0080 - 0.012 in/in | Across Flow; ISO 2577 |
| Melt Index of Compound | 5.0 g/10 min | 5.0 g/10 min | ISO 1133 |
| | @Load 2.16 kg, Temperature 230 °C | @Load 4.76 lb, Temperature 446 °F | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-------------------------|----------------------------|----------|
| Tensile Strength at Break | <= 27.0 MPa | <= 3920 psi | ISO/R527 |
| Elongation at Yield | 5.0 % | 5.0 % | ISO/R527 |
| Flexural Strength | <= 54.0 MPa | <= 7830 psi | ISO 178 |
| Flexural Modulus | 2.90 GPa | 421 ksi | ISO 178 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| Charpy Impact, Notched | 0.250 J/cm ² | 1.19 ft-lb/in ² | ISO 179 |
| | @Temperature -20.0 °C | @Temperature -4.00 °F | |
| | 0.400 J/cm ² | 1.90 ft-lb/in ² | ISO 179 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |

| Thermal Properties | Metric | English | Comments |
|---------------------------------------------|----------------|----------------|-------------------|
| Deflection Temperature at 0.46 MPa (66 psi) | 121 °C | 250 °F | 120°C/h; ISO 75/1 |
| Deflection Temperature at 1.8 MPa (264 psi) | 69.0 °C | 156 °F | 120°C/h; ISO 75/1 |
| Vicat Softening Point | 84.0 °C | 183 °F | 50°C/h; ISO 306 |
| | @Load 5.001 kg | @Load 11.03 lb | |

| Thermal Properties | Metric | English | Comments |
|--------------------|--------------------|----------------------|------------------|
| | @Load 1.00 kg | @Load 2.21 lb | 50 °C/h, ISO 306 |
| Flammability, UL94 | HB | HB | |
| | @Thickness 1.60 mm | @Thickness 0.0630 in | |
| Glow Wire Test | 750 °C | 1380 °F | IEC 695-2-1 |
| | @Thickness 2.00 mm | @Thickness 0.0787 in | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China