

Polykemi AB SCANAMID 66 A12^ F20 Nylon 66, Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-SCANAMID-66-A12-F20-Nylon-66-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ISO 1183
Filler Content	20 %	20 %	±2%; Polykemi
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	With Flow; ISO 2577
	0.012 cm/cm	0.012 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 140 MPa	<= 20300 psi	ISO/R527
Elongation at Yield	4.0 %	4.0 %	ISO/R527
Flexural Strength	<= 200 MPa	<= 29000 psi	ISO 178
Flexural Modulus	6.80 GPa	986 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	245 °C	473 °F	120°C/h; ISO 75/1
Vicat Softening Point	>= 230 °C	>= 446 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China