

## Polykemi AB SCANAMID 66 A52^E Nylon 66, Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-SCANAMID-66-A52E-Nylon-66-Modified.php](http://www.lookpolymers.com/polymer_Polykemi-AB-SCANAMID-66-A52E-Nylon-66-Modified.php)

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.016 cm/cm	0.016 in/in	With Flow; ISO 2577
	0.018 cm/cm	0.018 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	70	70	ASTM D2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength at Break	<= 50.0 MPa	<= 7250 psi	ISO/R527
Elongation at Break	55 %	55 %	ISO/R527
Elongation at Yield	8.0 %	8.0 %	ISO/R527
Flexural Strength	<= 90.0 MPa	<= 13100 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	4.00 J/cm <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	6.00 J/cm <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	180 °C	356 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	120°C/h; ISO 75/1
Vicat Softening Point	200 °C	392 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	

Thermal Properties	HB Metric	HB English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China