

## Polykemi AB SCANMID 6 B11^ F30 Nylon 6, Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

### Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polykemi-AB-SCANMID-6-B11-F30-Nylon-6-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Polykemi-AB-SCANMID-6-B11-F30-Nylon-6-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ISO 1183
Filler Content	30 %	30 %	±2%; Polykemi
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	With Flow; ISO 2577
	0.0090 cm/cm	0.0090 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	ASTM D2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength at Break	<= 160 MPa	<= 23200 psi	ISO/R527
Elongation at Yield	3.0 %	3.0 %	ISO/R527
Flexural Strength	<= 230 MPa	<= 33400 psi	ISO 178
Flexural Modulus	8.80 GPa	1280 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	120°C/h; ISO 75/1
Vicat Softening Point	215 °C	419 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Thermal Properties	650 °C Metric	1200 °F English	Comments
	@Thickness 2.00 mm	@Thickness 0.0787 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China