

## Polymax® Maxelast® P1970 TPE, PP Overmold or Standalone use

Category : Polymer , Thermoplastic , Elastomer, TPE , Polypropylene (PP)

### Material Notes:

Polymax's TPE material complies with UL, VDE, FDA, RoHS and PAH's standards. Uses: Consumer Products Toys & Novelties Auto Parts Tool Hand Grips Sporting Goods Wire & Cable Electronics Medical Devices Plastic Toughening Information from Alliance Polymers & Services, Distributor of Nantong Elastomer Technology Co.Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymax-Maxelast-P1970-TPE-PP-Overmold-or-Standalone-use.php](http://www.lookpolymers.com/polymer_Polymax-Maxelast-P1970-TPE-PP-Overmold-or-Standalone-use.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.992 g/cc	0.992 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Stress	3.41 MPa	495 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
Tensile Strength, Yield	4.36 MPa	632 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Tensile Strength, Yield	6.39 MPa	927 psi	ASTM D412
Elongation at Break	730 %	730 %	ASTM D412

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China