

Polymax® Maxelast® P2950T TPE, PP Overmold or Standalone use

Category : Polymer , Thermoplastic , Elastomer, TPE , Polypropylene (PP)

Material Notes:

Polymax's TPE material complies with UL, VDE, FDA, RoHS and PAH's standards. Uses: Consumer Products Toys & Novelties Auto Parts Tool Hand Grips Sporting Goods Wire & Cable Electronics Medical Devices Plastic Toughening Information from Alliance Polymers & Services, Distributor of Nantong Elastomer Technology Co.Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymax-Maxelast-P2950T-TPE-PP-Overmold-or-Standalone-use.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.902 g/cc	0.902 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.023 - 0.027 cm/cm	0.023 - 0.027 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Stress	2.14 MPa	310 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
Tensile Strength, Yield	3.14 MPa	455 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Tensile Strength, Yield	4.10 MPa	595 psi	ASTM D412
Elongation at Break	490 %	490 %	ASTM D412
Tear Strength	23.5 kN/m	134 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China