

## Polymax® Maxelast® P3950CT TPE, PP Overmold or Standalone use

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Polymax's TPE material complies with UL, VDE, FDA, RoHS and PAH's standards. Uses: Consumer Products Toys & Novelties Auto Parts Tool Hand Grips Sporting Goods Wire & Cable Electronics Medical Devices Plastic Toughening Information from Alliance Polymers & Services, Distributor of Nantong Elastomer Technology Co.Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymax-Maxelast-P3950CT-TPE-PP-Overmold-or-Standalone-use.php](http://www.lookpolymers.com/polymer_Polymax-Maxelast-P3950CT-TPE-PP-Overmold-or-Standalone-use.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.902 g/cc	0.902 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Stress	1.48 MPa	215 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
Tensile Strength, Yield	2.73 MPa	396 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Tensile Strength, Yield	5.76 MPa	835 psi	ASTM D412
Elongation at Break	690 %	690 %	ASTM D412

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China