

Polymer Resources NY6-G13 Nylon 6, 13% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 10% Glass Fiber Filled

Material Notes:

Nylon 6, 13% Glass Reinforced, Lubricated Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded (DAM). Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-NY6-G13-Nylon-6-13-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	131 MPa	19000 psi	ASTM D638
Tensile Strength, Yield	131 MPa	19000 psi	ASTM D638
Flexural Strength	165 MPa	24000 psi	ASTM D790
Flexural Modulus	5.24 GPa	760 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Temperature 22.8 °C	1.10 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	204 °C	400 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	199 °C	390 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	
	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 268 °C	480 - 515 °F	
Middle Barrel Temperature	243 - 260 °C	470 - 500 °F	

Front Barrel Temperature Processing Properties	249 - 268 °C Metric	480 - 515 °F English	Comments
Melt Temperature	249 - 268 °C	480 - 515 °F	
Mold Temperature	65.6 - 104 °C	150 - 220 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China