

## Polymer Resources NY6-G20 Nylon 6, 20% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 20% Glass Fiber Filled

### Material Notes:

Nylon 6, 20% Glass Reinforced, Lubricated Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded (DAM). Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-NY6-G20-Nylon-6-20-Glass-Reinforced.php](http://www.lookpolymers.com/polymer_Polymer-Resources-NY6-G20-Nylon-6-20-Glass-Reinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	177 MPa	25600 psi	ASTM D638
Tensile Strength, Yield	177 MPa	25600 psi	ASTM D638
Flexural Strength	265.1 MPa	38450 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Temperature 22.8 °C	2.00 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	216 °C	420 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	207 °C	405 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	
	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 268 °C	480 - 515 °F	
Middle Barrel Temperature	243 - 260 °C	470 - 500 °F	

Front Barrel Temperature Processing Properties	249 - 268 °C Metric	480 - 515 °F English	Comments
Melt Temperature	249 - 268 °C	480 - 515 °F	
Mold Temperature	65.6 - 104 °C	150 - 220 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China