

## Polymer Resources NY66-G20-MD Nylon 66, 20% Glass Reinforced with MoS2

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled , Nylon 66, MoS2 Filled

### Material Notes:

Nylon 66, 20% Glass Reinforced with Molybdenum Disulfide for Lubrication and Wear  
 Process: Injection Molding  
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded (DAM).  
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-NY66-G20-MD-Nylon-66-20-Glass-Reinforced-with-MoS2.php](http://www.lookpolymers.com/polymer_Polymer-Resources-NY66-G20-MD-Nylon-66-20-Glass-Reinforced-with-MoS2.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.013 cm/cm	0.0030 - 0.013 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ASTM D638
Tensile Strength, Yield	145 MPa	21000 psi	ASTM D638
Flexural Strength	228 MPa	33000 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Temperature 22.8 °C	1.50 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	254 °C	490 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	246 °C	475 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	
	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	266 - 288 °C	510 - 550 °F	
Middle Barrel Temperature	271 - 293 °C	520 - 560 °F	

Front Barrel Temperature Processing Properties	277 - 299 °C Metric	530 - 570 °F English	Comments
Melt Temperature	285 - 304 °C	545 - 580 °F	
Mold Temperature	93.3 - 110 °C	200 - 230 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China