

Polymer Resources NY66-GP2-[color]-H General Purpose Nylon 66, Nucleated, Heat Stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized , Nylon 66, Unreinforced

Material Notes:

General Purpose Nylon 66, Nucleated, Heat Stabilized Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded (DAM). Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-NY66-GP2-color-H-General-Purpose-Nylon-66-Nucleated-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Linear Mold Shrinkage	0.012 - 0.018 cm/cm	0.012 - 0.018 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	89.6 MPa	13000 psi	ASTM D638
Tensile Strength, Yield	89.6 MPa	13000 psi	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.03 GPa	440 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Temperature 22.8 °C	1.00 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	246 °C	475 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	102 °C	215 °F	ASTM D648
Flammability, UL94	V-2 @Thickness 1.59 mm	V-2 @Thickness 0.0626 in	
	V-2 @Thickness 3.17 mm	V-2 @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	266 - 277 °C	510 - 530 °F	

Middle Barrel Temperature Processing Properties	271 - 282 °C Metric	520 - 540 °F English	Comments
Front Barrel Temperature	277 - 288 °C	530 - 550 °F	
Melt Temperature	277 - 293 °C	530 - 560 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0003	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China