

## Polymer Resources NY66-IMG33 Nylon, 33% Glass Reinforced, Impact Modified (DAM)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

**Material Notes:**

Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Nylon grades are tested dry as molded (DAM). Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-NY66-IMG33-Nylon-33-Glass-Reinforced-Impact-Modified-DAM.php](http://www.lookpolymers.com/polymer_Polymer-Resources-NY66-IMG33-Nylon-33-Glass-Reinforced-Impact-Modified-DAM.php)

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	138 MPa	20000 psi	ASTM D638
Tensile Strength, Yield	138 MPa	20000 psi	ASTM D638
Flexural Strength	214 MPa	31000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	243 °C	470 °F	ASTM D648
Flammability, UL94	HB	HB	1/16 in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	293 - 304 °C	560 - 580 °F	
Middle Barrel Temperature	277 - 288 °C	530 - 550 °F	
Front Barrel Temperature	271 - 282 °C	520 - 540 °F	
Melt Temperature	288 - 299 °C	550 - 570 °F	
Mold Temperature	65.6 - 104 °C	150 - 220 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	

Processing Properties	Metric	English	Comments
Dry Time	3-4 hour	3-4 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China