

## Polymer Resources PC-GP3-TFE5 Polycarbonate, 5% PTFE, High Flow, Wear Resistant

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, PTFE Filled

### Material Notes:

Polycarbonate, General Purpose, High Flow, Wear Resistant Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-PC-GP3-TFE5-Polycarbonate-5-PTFE-High-Flow-Wear-Resistant.php](http://www.lookpolymers.com/polymer_Polymer-Resources-PC-GP3-TFE5-Polycarbonate-5-PTFE-High-Flow-Wear-Resistant.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	10 - 20 g/10 min @Load 1.20 kg, Temperature 300 °C	10 - 20 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	58.6 MPa	8500 psi	ASTM D638
Tensile Strength, Yield	58.6 MPa	8500 psi	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	2.24 GPa	325 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm @Temperature 22.8 °C	2.50 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	288 - 310 °C	550 - 590 °F	
Middle Barrel Temperature	299 - 321 °C	570 - 610 °F	
Front Barrel Temperature	310 - 332 °C	590 - 630 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	316 - 343 °C	600 - 650 °F	
Mold Temperature	82.2 - 116 °C	180 - 240 °F	
Drying Temperature	118 - 124 °C	245 - 255 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China