

Polymer Resources PC-IM2-UV Polycarbonate, Impact Modified, Medium Flow, UV-stabilized

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Impact Modified

Material Notes:

Polycarbonate, Impact Modified, Medium Flow, UV-stabilized
 Process: Injection Molding
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PC-IM2-UV-Polycarbonate-Impact-Modified-Medium-Flow-UV-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	9.0 - 16 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 - 16 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	53.8 MPa	7800 psi	ASTM D638
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Flexural Strength	79.3 MPa	11500 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	6.94 J/cm @Temperature -17.8 °C	13.0 ft-lb/in @Temperature 0.000 °F	ASTM D256
	8.01 J/cm @Temperature 22.8 °C	15.0 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	124 °C	255 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	118 °C	245 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	

Thermal Properties	^{HB} Metric	^{HB} English	Comments
	@Thickness 3.17 mm	@Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	254 - 277 °C	490 - 530 °F	
Middle Barrel Temperature	266 - 288 °C	510 - 550 °F	
Front Barrel Temperature	277 - 299 °C	530 - 570 °F	
Melt Temperature	274 - 302 °C	525 - 575 °F	
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	118 - 124 °C	245 - 255 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China