

Polymer Resources PC-UV2-D Polycarbonate, UV-stabilized, Medium Flow

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Polycarbonate, UV-stabilized, Medium Flow Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PC-UV2-D-Polycarbonate-UV-stabilized-Medium-Flow.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	9.0 - 16 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 - 16 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	72.4 MPa	10500 psi	ASTM D638
Tensile Strength, Yield	62.1 MPa	9000 psi	ASTM D638
Elongation at Break	140 %	140 %	ASTM D638
Elongation at Yield	6.5 %	6.5 %	ASTM D638
Flexural Strength	95.8 MPa	13900 psi	ASTM D790
Flexural Modulus	2.31 GPa	335 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm @Temperature 22.8 °C	15.0 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	135 °C	275 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	129 °C	265 °F	ASTM D648
Vicat Softening Point	152 °C	305 °F	120°C/h, 50 N; ASTM D1525

Thermal Properties	Metric	English	Comments
UL RTI, Electrical	80.0 °C	176 °F	UL 746
	@Thickness 0.749 mm	@Thickness 0.0295 in	
	120 °C	248 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	120 °C	248 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical with Impact	80.0 °C	176 °F	UL 746
	@Thickness 0.749 mm	@Thickness 0.0295 in	
	120 °C	248 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	120 °C	248 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	80.0 °C	176 °F	UL 746
	@Thickness 0.749 mm	@Thickness 0.0295 in	
	105 °C	221 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	110 °C	230 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	V-2	V-2	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-2	V-2	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Optical Properties	Metric	English	Comments
Haze	1.0 %	1.0 %	ASTM D1003
UV Transmittance	88 %	88 %	ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	11.8 kV/mm	300 kV/in	ASTM D149
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746

Electrical Properties	Metric ^{sec}	English ^{sec}	Comments
Hot Wire Ignition, HWI	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 746
	30 - 60 sec	30 - 60 sec	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	>= 120 arcs	>= 120 arcs	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	271 - 293 °C	520 - 560 °F	
Middle Barrel Temperature	282 - 304 °C	540 - 580 °F	
Front Barrel Temperature	293 - 316 °C	560 - 600 °F	
Melt Temperature	288 - 316 °C	550 - 600 °F	
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	118 - 124 °C	245 - 255 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Outdoor Suitability	f1	
Vent	0.0005	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China