

Polymer Resources PC/ABS-FR1-[color]-HH Flame Retardant PC/ABS Alloy, Low Flow

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

PC/ABS Alloy, Flame Retardant, Low Flow Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PCABS-FR1-color-HH-Flame-Retardant-PCABS-Alloy-Low-Flow.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	15 - 35 g/10 min @Load 5.00 kg, Temperature 250 °C	15 - 35 g/10 min @Load 11.0 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.1 MPa	9000 psi	ASTM D638
Tensile Strength, Yield	62.1 MPa	9000 psi	ASTM D638
Flexural Strength	93.1 MPa	13500 psi	ASTM D790
Flexural Modulus	2.69 GPa	390 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm @Temperature 22.8 °C	12.0 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	98.9 °C	210 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	
	V-0 - 5VA @Thickness 3.00 mm	V-0 - 5VA @Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	221 - 254 °C	430 - 490 °F	
Middle Barrel Temperature	232 - 266 °C	450 - 510 °F	
Front Barrel Temperature	243 - 277 °C	470 - 530 °F	
Melt Temperature	246 - 274 °C	475 - 525 °F	
Mold Temperature	48.9 - 82.2 °C	120 - 180 °F	
Drying Temperature	76.7 - 82.2 °C	170 - 180 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China