

Polymer Resources PCSF-FRG20 Polycarbonate, 20% Glass Reinforced Structural Foam Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 20% Glass Filled , Polycarbonate, Foam Grade, Glass Filled , Polycarbonate, Glass Fiber Filled, Flame Retardant

Material Notes:

Polycarbonate, 20% Glass Reinforced Structural Foam Grade Features: • Flame Retardant • Foamable • Self Extinguishing Process: Foam

Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PCSF-FRG20-Polycarbonate-20-Glass-Reinforced-Structural-Foam-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	ASTM D955
Melt Flow	4.0 - 10 g/10 min @Load 1.20 kg, Temperature 300 °C	4.0 - 10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	117 MPa	17000 psi	ASTM D638
Tensile Strength, Yield	117 MPa	17000 psi	ASTM D638
Flexural Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	5.17 GPa	750 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Temperature 22.8 °C	1.50 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	141 °C	285 °F	ASTM D648
Flammability, UL94	V-2 @Thickness 1.59 mm	V-2 @Thickness 0.0626 in	
	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	293 - 316 °C	560 - 600 °F	
Middle Barrel Temperature	304 - 327 °C	580 - 620 °F	
Front Barrel Temperature	316 - 338 °C	600 - 640 °F	
Melt Temperature	302 - 329 °C	575 - 625 °F	
Mold Temperature	82.2 - 116 °C	180 - 240 °F	
Drying Temperature	118 - 124 °C	245 - 255 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China