

## Polymer Resources PC/TP-GP1-HF PC/Polyester Alloy, High Melt Flow

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP

### Material Notes:

High Melt Flow, Good Chemical Resistance  
 Process: Injection Molding  
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.  
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-PCTP-GP1-HF-PCPolyester-Alloy-High-Melt-Flow.php](http://www.lookpolymers.com/polymer_Polymer-Resources-PCTP-GP1-HF-PCPolyester-Alloy-High-Melt-Flow.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
Melt Flow	15 - 20 g/10 min @Load 2.16 kg, Temperature 265 °C	15 - 20 g/10 min @Load 4.76 lb, Temperature 509 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	51.7 MPa	7500 psi	ASTM D638
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Flexural Strength	68.9 MPa	10000 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Temperature 22.8 °C	2.00 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	
	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 271 °C	480 - 520 °F	
Middle Barrel Temperature	254 - 277 °C	490 - 530 °F	
Front Barrel Temperature	260 - 282 °C	500 - 540 °F	
Melt Temperature	246 - 274 °C	475 - 525 °F	
Mold Temperature	65.6 - 87.8 °C	150 - 190 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China