

Polymer Resources PC/TP-GP3-G20 PC/Polyester Alloy, 20% Glass Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend, Glass Reinforced , Polyester, TP

Material Notes:

Superior Chemical Resistance, 20% Glass Reinforced
 Process: Injection Molding
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PCTP-GP3-G20-PCPolyester-Alloy-20-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
Melt Flow	1.0 - 8.0 g/10 min @Load 2.16 kg, Temperature 265 °C	1.0 - 8.0 g/10 min @Load 4.76 lb, Temperature 509 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.8 MPa	11000 psi	ASTM D638
Tensile Strength, Yield	75.8 MPa	11000 psi	ASTM D638
Flexural Strength	110 MPa	16000 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm @Temperature 22.8 °C	3.00 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	179 °C	355 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0626 in	
	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 271 °C	480 - 520 °F	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	254 - 277 °C	480 - 530 °F	
Front Barrel Temperature	260 - 282 °C	500 - 540 °F	
Melt Temperature	260 - 288 °C	500 - 550 °F	
Mold Temperature	65.6 - 87.8 °C	150 - 190 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China