

Polymer Resources PPX-GP1-[color]-EN Modified-PPO, Extrusion Grade

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, Extruded

Material Notes:

Modified-Polyphenylene Oxide, Extrusion Grade, 265F HDT
 Features: • Hydrolytically Stable • Low to No Water Absorption
 Process: Extrusion
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-GP1-color-EN-Modified-PPO-Extrusion-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	4.0 - 9.0 g/10 min @Load 11.6 kg, Temperature 250 °C	4.0 - 9.0 g/10 min @Load 25.6 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength at Break	48.3 MPa	7000 psi	ASTM D638
Tensile Strength, Yield	55.2 MPa	8000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm @Temperature -30.0 °C	2.50 ft-lb/in @Temperature -22.0 °F	ASTM D256
	2.14 J/cm @Temperature 22.8 °C	4.00 ft-lb/in @Temperature 73.0 °F	ASTM D256
Charpy Impact, Notched	1.47 J/cm ² @Temperature 22.8 °C	7.00 ft-lb/in ² @Temperature 73.0 °F	ISO 179/1eA
Gardner Impact	16.9 J	12.5 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties (Stress at 0.46 MPa (66 psi))	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	121 °C	250 °F	ASTM D648
Vicat Softening Point	146 °C	295 °F	120°C/h, 50 N; ASTM D1525
UL RTI, Electrical	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical with Impact	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical without Impact	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL 746
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	>= 204 °C	>= 400 °F	
Middle Barrel Temperature	>= 227 °C	>= 440 °F	
Front Barrel Temperature	>= 227 °C	>= 440 °F	
Melt Temperature	227 - 254 °C	440 - 490 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China