

## Polymer Resources PPX-GP4 Modified-PPO, General Purpose

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, Molded

### Material Notes:

Modified-Polyphenylene Oxide, General Purpose, 210F HDT  
 Process: Injection Molding  
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.  
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-PPX-GP4-Modified-PPO-General-Purpose.php](http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-GP4-Modified-PPO-General-Purpose.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	20 - 30 g/10 min @Load 11.6 kg, Temperature 250 °C	20 - 30 g/10 min @Load 25.6 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	34.5 MPa	5000 psi	ASTM D638
Tensile Strength, Yield	34.5 MPa	5000 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	48.3 MPa	7000 psi	ASTM D790
Flexural Modulus	1.76 GPa	255 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm @Temperature -30.0 °C	2.50 ft-lb/in @Temperature -22.0 °F	ASTM D256
	2.67 J/cm @Temperature 22.8 °C	5.00 ft-lb/in @Temperature 73.0 °F	ASTM D256
Charpy Impact, Notched	1.57 J/cm <sup>2</sup> @Temperature 22.8 °C	7.50 ft-lb/in <sup>2</sup> @Temperature 73.0 °F	ISO 179/1eA
Gardner Impact	14.1 J	10.4 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	98.9 °C	210 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648

Thermal Properties Flammability, UL 94	<sup>MP</sup> Metric	<sup>MP</sup> English	Comments
	@Thickness 1.59 mm	@Thickness 0.0626 in	
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 299 °C	480 - 570 °F	
Middle Barrel Temperature	260 - 304 °C	500 - 580 °F	
Front Barrel Temperature	271 - 310 °C	520 - 590 °F	
Melt Temperature	288 - 316 °C	550 - 600 °F	
Mold Temperature	71.1 - 98.9 °C	160 - 210 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China