

## Polymer Resources TP-FR IM2 PBT, Impact Modified, Flame Retardant, High Flow

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Impact Grade

### Material Notes:

Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.

Information provided by Polymer Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polymer-Resources-TP-FR-IM2-PBT-Impact-Modified-Flame-Retardant-High-Flow.php](http://www.lookpolymers.com/polymer_Polymer-Resources-TP-FR-IM2-PBT-Impact-Modified-Flame-Retardant-High-Flow.php)

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.010 - 0.014 cm/cm	0.010 - 0.014 in/in	ASTM D955
Melt Flow	8.0 - 15 g/10 min	8.0 - 15 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	37.9 MPa	5500 psi	ASTM D638
Tensile Strength, Yield	37.9 MPa	5500 psi	ASTM D638
Flexural Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm	12.0 ft-lb/in	ASTM D256
Gardner Impact	>= 36.2 J	>= 26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	127 °C	260 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	118 °C	245 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/16 in
	V-0	V-0	1/8 in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	238 - 254 °C	460 - 490 °F	
Middle Barrel Temperature	243 - 260 °C	470 - 500 °F	
Front Barrel Temperature	249 - 266 °C	480 - 510 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	246 - 274 °C	475 - 525 °F	
Mold Temperature	48.9 - 76.7 °C	120 - 170 °F	
Drying Temperature	116 - 121 °C	240 - 250 °F	
Dry Time	3 - 4 hour	3 - 4 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China