

Polyplastic TechnoTep B® 65 A Thermoplastic Elastomer, Mineral Filled

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

High mineral filled, weather stability Information provided by PolyPlastic Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastic-TechnoTep-B-65-A-Thermoplastic-Elastomer-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Melt Flow	3.5 g/10 min @Load 5.00 kg, Temperature 190 °C	3.5 g/10 min @Load 11.0 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ISO 868
Tensile Strength at Break	5.50 MPa	798 psi	ISO 37
Elongation at Break	750 %	750 %	ISO 37
Compression Set	50 % @Temperature 70.0 °C, Time 79200 sec	50 % @Temperature 158 °F, Time 22.0 hour	ASTM D 395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	Dynamic
	135 °C	275 °F	Static
Brittleness Temperature	-55.0 °C	-67.0 °F	

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 200 °C	374 - 392 °F	
Mold Temperature	10.0 - 50.0 °C	50.0 - 122 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China