

Polyplastics Duracon® TD-25 Acetal Co-polymer (POM), High impact, Flexible

Category: Polymer, Thermoplastic, Acetal (POM), Acetal Copolymer, Impact Modified

Material Notes:

DURACON® is a crystalline thermoplastic acetal copolymer. The primary raw material trioxane, a trimer of formaldehyde. The thermoplastic adopts a copolymer structure in which polyoxymethylene (-C-O) and carbon-carbon (-C-C- bond) comonomer groups are incorporated into its main chain. Therefore the copolymer has superior chemical and thermal stability, compared with acetal homopolymer. Acetal co-polymer is well-balanced in terms of mechanical, chemical and thermal properties, and its superior moldability allows it to be widely employed in various industrial fields. Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duracon-TD-25-Acetal-Co-polymer-POM-High-impact-Flexible.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	35.0 MPa	5080 psi	ISO 527-1,2
Elongation at Break	100 %	100 %	ISO 527-1,2
Flexural Strength	42.0 MPa	6090 psi	ISO 178
Flexural Modulus	1.20 GPa	174 ksi	ISO 178
Charpy Impact, Notched	1.54 J/cm ²	7.33 ft-lb/in²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ISO 75-1, 2
Flammability, UL94	НВ	НВ	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China