

Polyplastics Duranex® 304SA Polybutylene Terephthalate (PBT), Low density, Low wear, GF filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Filled, Impact Modified

Material Notes:

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value. Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duranex-304SA-Polybutylene-Terephthalate-PBT-Low-density-Low-wear-GF-filled.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	96.1 MPa	13900 psi	ISO 527-1, 2
Elongation at Break	2.3 %	2.3 %	ISO 527-1, 2
Flexural Strength	139 MPa	20200 psi	ISO 178
Flexural Modulus	5.31 GPa	770 ksi	ISO 178
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ISO 75-1, 2
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	IEC 60093
Surface Resistance	8.00e+15 ohm	8.00e+15 ohm	IEC 60093
Dielectric Strength	24.0 kV/mm	610 kV/in	IEC 60243-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China