

Polyplastics Duranex® 7307 Polybutylene Terephthalate (PBT), Super low warpage, GF filled

Category: Polymer, Thermoplastic, Polyester, TP, Polybutylene Terephthalate (PBT), Polybutylene Terephthalate (PBT), Glass Filled, Impact Modified

Material Notes:

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value.Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duranex-7307-Polybutylene-Terephthalate-PBT-Super-low-warpage-GF-filled.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	106 MPa	15400 psi	ISO 527-1,2
Elongation at Break	2.8 %	2.8 %	ISO 527-1,2
Flexural Strength	168 MPa	24400 psi	ISO 178
Flexural Modulus	6.50 GPa	943 ksi	ISO 178
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 μm/m-°C	16.7 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ISO 75-1, 2
Flammability, UL94	НВ	НВ	



Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China