

## Polyplastics TOPAS® 6017 Cyclic Olefin Copolymer (COC) (Asia/Pacific Grade)

Category : Polymer , Thermoplastic , Cyclo Olefin Polymer

### Material Notes:

Possesses the highest heat resistance among cyclic olefin-type resins. Information provided by PolyPlastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyplastics-TOPAS-6017-Cyclic-Olefin-Copolymer-COC-AsiaPacific-Grade.php](http://www.lookpolymers.com/polymer_Polyplastics-TOPAS-6017-Cyclic-Olefin-Copolymer-COC-AsiaPacific-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.010 %	0.010 %	immersion @23°C; ISO 62
Water Vapor Transmission	0.0450 g/m <sup>2</sup> /day	0.00290 g/100 in <sup>2</sup> /day	[g·mm/m<sup>2</sup>·d] @ 23°C and 85% RH; DIN 53122
	0.250 g/m <sup>2</sup> /day	0.0161 g/100 in <sup>2</sup> /day	Good barrier properties
Melt Flow	1.5 g/10 min	1.5 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 260 °C	@Load 4.76 lb, Temperature 500 °F	
	5.0 g/10 min	5.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 245 °C	@Load 4.76 lb, Temperature 473 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	58.0 MPa	8410 psi	5mm/min; ISO 527-1, 2
Elongation at Break	2.4 %	2.4 %	5mm/min; ISO 527-1, 2
Tensile Modulus	3.00 GPa	435 ksi	1mm/min; ISO 527-1, 2
Charpy Impact Unnotched	1.50 J/cm <sup>2</sup>	7.14 ft·lb/in <sup>2</sup>	ISO 179/1eU
Charpy Impact, Notched	0.160 J/cm <sup>2</sup>	0.761 ft·lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	170 °C	338 °F	
Deflection Temperature at 1.8 MPa (264 psi)	151 °C	304 °F	ISO 75-1, 2
Glass Transition Temp, Tg	180 °C	356 °F	

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Refractive Index Optical Properties	1.53 Metric	1.53 English	Comments
Transmission, Visible	91 %	91 %	ISO 13468-1

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.2	2.2	
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	
Dissipation Factor	0.00010	0.00010	
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	

Descriptive Properties	Value	Comments
Pencil Hardness	F	JIS K5401
Resistance to Acids	Usable	
Resistance to Alcohols	Usable	
Resistance to Alkalis	Usable	
Resistance to Aromatic Solvents	Not Usable	
Resistance to Chlorinated Solvents	Not Usable	
Resistance to Esters	Usable	
Resistance to Gasoline	Not Usable	
Resistance to Ketones	Usable	
Resistance to Oils	Not Usable	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China