

## Polyram BondyRam® 2001 Maleic Anhydride modified EVA coupling agent (discontinued \*\*)

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Ethylene Vinyl Acetate

**Material Notes:**

Maleic Anhydride Modified grafted EVA (28%VA) recommended as adhesive promoter and general purpose compatibilizerInformation provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-BondyRam-2001-Maleic-Anhydride-modified-EVA-coupling-agent-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Polyram-BondyRam-2001-Maleic-Anhydride-modified-EVA-coupling-agent-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in <sup>3</sup>	ASTM D-792
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Thermal Properties	Metric	English	Comments
Melting Point	73.0 °C	163 °F	DSC

Descriptive Properties	Value	Comments
Maleic Anhydride Level	0.5	By FTIR

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China