

Polyram BondyRam® 4001 Maleic Anhydride modified LLDPE coupling agent (discontinued **)

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Maleic Anhydride grafted linear low density polyethylene recommended as a coupling agent in PE composites with minerals and wood and compatibilizer in PE/PA blends. Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-BondyRam-4001-Maleic-Anhydride-modified-LLDPE-coupling-agent-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D-792
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 190 °C	4.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Thermal Properties	Metric	English	Comments
Vicat Softening Point	100 °C	212 °F	ASTM-D1525

Descriptive Properties	Value	Comments
Maleic Anhydride Level	0.7	By FTIR

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China