

Polyram BondyRam® 6000 Maleic Anhydride grafted Acrylonitrile-Butadiene-Styrene coupling agent

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic , ABS Polymer

Material Notes:

Maleic Anhydride grafted Acrylonitrile-Butadiene-Styrene recommended as coupling agent in Styrene composites with glass or other minerals. Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-BondyRam-6000-Maleic-Anhydride-grafted-Acrylonitrile-Butadiene-Styrene-coupling-agent.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ASTM D-792
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Thermal Properties	Metric	English	Comments
Vicat Softening Point	97.0 °C	207 °F	ASTM-D1525

Descriptive Properties	Value	Comments
Maleic Anhydride Level	0.7	By FTIR

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China