

## Polyram BondyRam® 7001 Maleic Anhydride Modified Semi-crystalline EPDM Impact Modifier

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic

### Material Notes:

Maleic Anhydride Modified Semi-crystalline EPDM recommended as impact modifier for polyamide compounds. Information provided by Polyram Ram On Ind.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polyram-BondyRam-7001-Maleic-Anhydride-Modified-Semi-crystalline-EPDM-Impact-Modifier.php](http://www.lookpolymers.com/polymer_Polyram-BondyRam-7001-Maleic-Anhydride-Modified-Semi-crystalline-EPDM-Impact-Modifier.php)

Physical Properties	Metric	English	Comments
Density	0.870 g/cc	0.0314 lb/in <sup>3</sup>	ASTM D-792
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Descriptive Properties	Value	Comments
Maleic Anhydride Level	0.7	By FTIR

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China