

Polyram Bondyram® 1004 Maleic Anhydride Modified Homo-Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Recommended for coupling of wood in polypropylene composites. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-Bondyram-1004-Maleic-Anhydride-Modified-Homo-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ISO 1183
Melt Flow	>= 150 g/10 min @Load 2.16 kg, Temperature 190 °C	>= 150 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	160 °C	320 °F	ISO 11357

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China